

**Description**

BLUESIL SP 3309 is a polyether modified trisiloxane.

**Examples of applications**

BLUESIL SP 3309 is a super wetting agent that can be used in many applications such as :

- Agrochemicals
- Fiber treatment
- Surface modification
- Leather treatment

**Key benefits**

- Excellent wetting properties
- High spreading rate
- Improves the adherence of coatings
- Improve spray coverage
- High surface activity
- Affinity with various surfaces
- Low viscosity provides easy handling

**Typical properties**

Aspect	Liquid
Color	Water white to straw
Density at 25°C, g/cm <sup>3</sup> , approx	1.02
Viscosity at 25°C, mPa.s, approx	35
Surface tension, 25°C 0.1% in water, mN/m, approx	20.1

Please note: The typical properties are not intended for use in preparing specifications. Please contact our local Sales Department for assistance in writing specifications.

**Instruction of use**

BLUESIL™ SP 3309 is water dispersible at ambient temperature.

**Regulation**

Please consult your local ELKEM SILICONES sales office.

**Limitations**

Please consult your local ELKEM SILICONES sales office.

**Packaging**

- BLUESIL SP 3309 is available in

# BLUESIL SP 3309

Technical Data Sheet n° 2657-V6 – 2019/04/30

- Drum of 200 KG (441 LB)
- Pail of 25 KG (55.13 LB)

---

**Storage and shelf life**

When stored in its original packaging:

BLUESIL SP 3309 may be stored at a temperature between -5 °C/ 23 °F and 40 °C/ 104 °F for up to 36 months from its date of manufacturing.

Comply with the storage instructions and expiration date marked on the packaging. Beyond this date, Elkem Silicones no longer guarantees that the product meets the sales specifications.

---

**Safety**

Please consult the Safety Data Sheet of:  
BLUESIL SP 3309

---

Visit our website [www.silicones.elkem.com](http://www.silicones.elkem.com)

**Warning to the users**

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELKEM SILICONES is at their disposal to supply any additional information.